

Typical Data		SPECIAL GRADES			
		C-22 Z	BNZ-24	BNZ-25	BNZ-26 HS
Properties					
Temperature Use Limit	^{°F}	2300	2400	2500	2600
(Normal oxidizing atmosphere)	^{°C}	1260	1316	1371	1427
Density, Avg.	<i>lb/ft³</i>	46	37	45	57
ASTM C 134	<i>kg/m³</i>	737	593	721	913
	<i>lb/BEq</i>	2.7	2.2	2.6	3.3
	<i>kg/str.</i>	1.2	1.0	1.2	1.5
Modulus of Rupture	<i>lb/in²</i>	210	120	150	360
ASTM C 133	<i>MPa</i>	1.4	0.8	1.0	2.5
	<i>kg/cm²</i>	14.8	8.5	10.6	25.4
Cold Crushing of Strength	<i>lb/in²</i>	320	130	260	580
ASTM C 133	<i>MPa</i>	2.2	0.9	1.8	4.0
	<i>kg/cm²</i>	22.5	9.2	18.3	40.8
Permanent Linear Change	%				
ASTM C 210					
24 hrs at soaking temp: ^{°F} (^{°C})					
2250 (1232)		0.0	-	-	-
2350 (1290)		-	-0.4	-	-
2450 (1343)		-	-	-0.4	-
2550 (1399)		-	-	-	-0.7
2750 (1510)		-	-	-	-
2800 (1538)		-	-	-	-
2950 (1621)		-	-	-	-
3150 (1732)		-	-	-	-
Reversible Linear Thermal Expansion	%				
at 2000 ^{°F} (1093 ^{°C})		0.5	0.6	0.6	0.6
Hot Load Strength	%				
ASTM C 16	deformation				
10 psi load for 11/2 hours: ^{°F} (^{°C})					
2000 (1093)		0.1	0	-	-
2200 (1204)		-	-	0.3	0.1
2400 (1316)		-	-	-	-
Thermal Conductivity	Btu-in/ft ² , hr, ^{°F}				
ASTM C 182	(W/mk)				
Mean temperature, ^{°F} (^{°C})					
500		1.5	0.9	1.8	1.9
(260)		0.22	0.13	0.26	0.27
1000		1.8	1.1	2.1	2.2
(538)		0.26	0.16	0.30	0.32
1500		2.2	1.4	2.5	2.5
(816)		0.32	0.20	0.36	0.36
2000		2.5	1.6	2.8	2.8
(1093)		0.36	0.23	0.40	0.40
To convert Btu-in/ft ² , hr, ^{°F} to Kcal-m ² , hr, ^{°C} , multiply by 0.124.					
Chemical Analysis					
Alumina – Al ₂ O ₃		35	40.0	34.0	44.7
Silica – SiO ₂		60.1	47.2	63.0	49.9
Ferric Oxide – Fe ₂ O ₃		1.1	0.5	0.7	0.6
Titanium Oxide – Ti ₂ O ₂		1.3	1.5	1.4	1.6
Calcium Oxide – CaO		2.1	10.3	0.3	0.6
Magnesium Oxide – MgO		0.0	0.2	0.1	0.1
Alkalies, as Na ₂ O & K ₂ O		0.4	0.3	0.5	2.5

*ASTM C 113