

Typical Data		STANDARD ASTM C 155 GRADES								
Properties		BNZ-20	BNZ-23	BNZ-23 HS	BNZ-23A	BNZ-26	BNZ-26-60	BNZ-28	BNZ-3000	BNZ-32
ASTM Classification		20/23	23	23	23	26	26	28	30	32
Temperature Use Limit (Normal oxidizing atmosphere)		°F 1260	2300 1260	2300 1260	2300 1260	2600 1427	2600 1427	2800 1538	3000 1649	3200 1760
Density, Avg. ASTM C 134		lb/ft ² kg/m ²	36 577	37 593	42 673	33 529	48 769	50 801	55 881	65 1041
		lb/BEq kg/str.	2.1 0.9	2.2 1.0	2.5 1.1	1.93 0.86	2.8 1.3	2.9 1.3	3.2 1.5	3.8 1.7
Modulus of Rupture ASTM C 133		lb/in ² MPa	95 0.7	105 0.7	140 1.0	115 0.79	200 1.4	190 1.3	220 1.5	250 1.7
		kg/cm ²	6.7	7.4	9.9	8	14.1	13.4	15.5	20.1
Cold Crushing of Strength ASTM C 133		lb/in ² MPa	105 0.7	125 0.9	190 1.3	145 1	270 1.9	290 2.0	340 2.3	440 3.0
		kg/cm ²	7.4	8.8	13.4	10.2	19.0	20.4	23.9	31.0
Permanent Linear Change ASTM C 210		%								
24 hrs at soaking temp: °F (°C)										
2250 (1232)		0.0	0.0	0.0	0.0	-	-	-	-	-
2350 (1290)		-	-	-	-	-	-	-	-	-
2450 (1343)		-	-	-	-	-	-	-	-	-
2550 (1399)		-	-	-	-	-0.1	-0/2	-	-	-
2750 (1510)		-	-	-	-	-	-	-0.7	-	-
2800 (1538)		-	-	-	-	-	-	-	-	-
2950 (1621)		-	-	-	-	-	-	-0.7	-	-
3150 (1732)		-	-	-	-	-	-	-	-0.4	-
Reversible Linear Thermal Expansion		%								
at 2000°F (1093°C)		0.6	0.6	0.6	0.6	0.6	0.6	0.65	0.65	0.65
Hot Load Strength ASTM C 16		% deformation								
10 psi load for 11/2 hours: °F (°C)										
2000 (1093)		0	0	0	0	-	-	-	-	-
2200 (1204)		-	-	-	-	0.2	0.1	0.1	-	-
2400 (1316)		-	-	-	-	-	-	0.3	0.2	-
Thermal Conductivity ASTM C 182		Btu-in/ft ² , hr, °F (W/mk)								
Mean temperature, °F (°C)										
500 (260)		0.9 0.13	1.0 0.14	1.2 0.17	.92 0.13	1.6 0.23	1.8 0.26	2.3 0.33	2.8 0.40	3.9 0.56
1000 (538)		1.2 0.17	1.3 0.19	1.5 0.22	1.14 0.16	1.9 0.27	2.0 0.29	2.4 0.35	2.9 0.42	4.1 0.59
1500 (816)		1.5 0.22	1.6 0.23	1.7 0.25	1.39 0.2	2.2 0.32	2.1 0.30	2.6 0.37	3.1 0.45	4.2 0.61
2000 (1093)		1.7 0.24	1.8 0.26	2.0 0.29	1.64 0.24	2.6 0.37	2.3 0.33	2.7 0.39	3.3 0.48	4.3 0.62
To convert Btu-in/ft ² , hr, °F to Kcal-m ² , hr, °C, multiply by 0.124.										
Chemical Analysis										
Alumina – Al ₂ O ₃		35	35	35	38	47.0	60.4	67.0	69.9	78.3
Silica – SiO ₂		60.3	60.3	60.3	45	48.6	36.1	30.5	28.1	20.7
Ferric Oxide – Fe ₂ O ₃		.9	0.9	0.9	0.3	0.7	0.4	0.3	0.3	0.2
Titanium Oxide – Ti ₂ O ₂		1.3	1.3	1.3	1.6	1.3	1.0	0.9	1.2	0.5
Calcium Oxide – CaO		2.1	2.1	2.1	15	0.3	0.1	0.3	0.2	0.1
Magnesium Oxide – MgO		0.0	0.0	0.0	0.1	0.1	0.2	0.0	0.1	0.1
Alkalies, as Na ₂ O & K ₂ O		0.4	0.4	0.4	0.5	2.0	1.8	1.0	0.2	0.1