

Typical Data	STANDARD ASTM C 155 GRADES									
	BNZ-20	BNZ-23	BNZ-23 HS	BNZ-23A	BNZ-26	BNZ-26-60	BNZ-28	BNZ-3000	BNZ-32	
Properties										
ASTM Classification	20/23	23	23	23	26	26	28	30	32	
Temperature Use Limit (Normal oxidizing atmosphere)	°F °C	2300 1260	2300 1260	2300 1260	2300 1260	2600 1427	2600 1427	2800 1538	3200 1760	
Density, Avg. ASTM C 134	lb/ft <sup>2</sup> kg/m <sup>2</sup> lb/BEq kg/str.	36 577 2.1 0.9	37 593 2.2 1.0	42 673 2.5 1.1	33 529 1.93 0.86	48 769 2.8 1.3	50 801 2.9 1.3	55 881 3.2 1.3	65 1041 3.8 1.7	75 1201 4.4 2.0
Modulus of Rupture ASTM C 133	lb/in <sup>2</sup> MPa kg/cm <sup>2</sup>	95 0.7 6.7	105 0.7 7.4	140 1.0 9.9	115 0.79 8	200 1.4 14.1	190 1.3 13.4	220 1.5 15.5	250 1.7 17.6	300 2.1 21.1
Cold Crushing of Strength ASTM C 133	lb/in <sup>2</sup> MPa kg/cm <sup>2</sup>	105 0.7 7.4	125 0.9 8.8	190 1.3 13.4	145 1 10.2	270 1.9 19.0	290 2.0 20.4	340 2.3 23.9	440 3.0 31.0	450 3.1 31.7
Permanent Linear Change	%									
ASTM C 210										
24 hrs at soaking temp: °F (°C)										
2250 (1232)	0.0	0.0	0.0	0.0	-	-	-	-	-	
2350 (1290)	-	-	-	-	-	-	-	-	-	
2450 (1343)	-	-	-	-	-	-	-	-	-	
2550 (1399)	-	-	-	-	-0.1	-0/2	-	-	-	
2750 (1510)	-	-	-	-	-	-	-0.7	-	-	
2800 (1538)	-	-	-	-	-	-	-	-	-	
2950 (1621)	-	-	-	-	-	-	-	-0.7	-	
3150 (1732)	-	-	-	-	-	-	-	-	-0.4	
Reversible Linear Thermal Expansion	%									
at 2000°F (1093°C)	0.6	0.6	0.6	0.6	0.6	0.6	0.65	0.65	0.65	
Hot Load Strength	%									
ASTM C 16	deformation									
10 psi load for 11/2 hours: °F (°C)										
2000 (1093)	0	0	0	0	-	-	-	-	-	
2200 (1204)	-	-	-	-	0.2	0.1	0.1	-	-	
2400 (1316)	-	-	-	-	-	-	-	0.3	0.2	
Thermal Conductivity	Btu-in/ft <sup>2</sup> , hr, °F									
ASTM C 182	(W/mk)									
Mean temperature, °F (°C)										
500	0.9	1.0	1.2	.92	1.6	1.8	2.3	2.8	3.9	
(260)	0.13	0.14	0.17	0.13	0.23	0.26	0.33	0.40	0.56	
1000	1.2	1.3	1.5	1.14	1.9	2.0	2.4	2.9	4.1	
(538)	0.17	0.19	0.22	0.16	0.27	0.29	0.35	0.42	0.59	
1500	1.5	1.6	1.7	1.39	2.2	2.1	2.6	3.1	4.2	
(816)	0.22	0.23	0.25	0.2	0.32	0.30	0.37	0.45	0.61	
2000	1.7	1.8	2.0	1.64	2.6	2.3	2.7	3.3	4.3	
(1093)	0.24	0.26	0.29	0.24	0.37	0.33	0.39	0.48	0.62	
To convert Btu-in/ft <sup>2</sup> , hr,										
°F to Kcal-m <sup>2</sup> , hr, °C, multiply by 0.124.										
Chemical Analysis										
Alumina – Al <sub>2</sub> O <sub>3</sub>	35	35	35	38	47.0	60.4	67.0	69.9	78.3	
Silica – SiO <sub>2</sub>	60.3	60.3	60.3	45	48.6	36.1	30.5	28.1	20.7	
Ferric Oxide – Fe <sub>2</sub> O <sub>3</sub>	0.9	0.9	0.9	0.3	0.7	0.4	0.3	0.3	0.2	
Titanium Oxide – Ti <sub>2</sub> O <sub>2</sub>	1.3	1.3	1.3	1.6	1.3	1.0	0.9	1.2	0.5	
Calcium Oxide – CaO	2.1	2.1	2.1	15	0.3	0.1	0.3	0.2	0.1	
Magnesium Oxide – MgO	0.0	0.0	0.0	0.1	0.1	0.2	0.0	0.1	0.1	
Alkalies, as Na <sub>2</sub> O & K <sub>2</sub> O	0.4	0.4	0.4	0.5	2.0	1.8	1.0	0.2	0.1	